

# KAPA®

## KAPA color

### Product Datasheet / Issue 08/11 / Replaces Issue 01/08

#### Characteristics:

<b>application:</b>	KAPA® color is a base plate for all creative work, modelling and presentation plate; base plate for passepartout and presentation use
<b>panel construction:</b>	sandwich-element with PUR-rigid foam core, plastic-coated cellucarton covering layers (bicolor versions)
<b>behaviour in external conditions:</b>	The board is not flame retardant The foam shows no water absorption, only in cut cells. The layer is not moisture-sensitive.
<b>chemical effects:</b>	The foam is resistant against solvents and glues. For glues with toluol please make trials. The layer is resistant against glues and inks.
<b>behaviour against thermal effects:</b>	Sheet processing temperature continuous $T_d = -20^{\circ}\text{C}$ up to $100^{\circ}\text{C}$ short-term $T_k =$ up to $160^{\circ}\text{C}$
<b>additional compliance to following standards:</b>	Certificate DIN ISO 9001:2008 Certificate DIN ISO 14001:2004 OHSAS 18001:2007 Development, manufacturing and sales of lightweight boards and PUR-forming parts

All data are based on our current knowledge and experience. They are considered as a reference without being legally binding.



3A Composites GmbH  
Kiefernweg 10  
49090 Osnabrück, Germany  
[display.eu@3AComposites.com](mailto:display.eu@3AComposites.com)  
[www.display.3AComposites.com](http://www.display.3AComposites.com)



KAPA color

Technical Datasheet / Issue 08/11 / Replaces Issue 01/08

Technical Data an Tolerances:

attribute	value		tolerance	unit	method
thickness	3,0	5,0	± 0,6	mm	KAPA-Meth.
density	60	55	± 3	kg/m <sup>3</sup>	KAPA-Meth.
weight per unit area	775	870	-	g/m <sup>2</sup>	KAPA-Meth.
compression strength 10% compression set	~ 0,08	~ 0,19	-	N/mm <sup>2</sup>	DIN 53421
memory effect 10% compression set	~ 100	~ 98	-	%	DIN 53421
elastic modulus (E-Modul)	~ 2,85	~ 5,82	-	N/mm <sup>2</sup>	DIN 53421
bending strength	~ 9,32	~ 4,97	-	N/mm <sup>2</sup>	DIN 53423
closed cell structure	> 95			-	KAPA-Meth.
ph-value	6,6			-	DIN 53124

Packaging Units:

thickness in mm	3	5		
sizes in mm	sheets per Box		tolerance	right angle
500 x 700	40*	24**	± 1 mm	± 1 mm/m
1000 x 700		24**	± 1 mm	± 1 mm/m
1000 x 1400		24**	± 1 mm	± 1 mm/m

\* only in bicolor (black and grey surface)

\*\* also in bicolor and black /black and grey/grey

All data are based on our current knowledge and experience. They are considered as a reference without being legally binding.



3A Composites GmbH  
Kiefernweg 10  
49090 Osnabrück, Germany  
[display.eu@3AComposites.com](mailto:display.eu@3AComposites.com)  
[www.display.3AComposites.com](http://www.display.3AComposites.com)