

## Description

Three-layered, light yellow, cadmium-free, high-performance PVC film with a glossy surface finish. Conforms to the stipulations of German standard DIN 67510. The afterglow effect is characterised by a particularly marked initial brightness after the active light source has been switched off. This process can be repeated as often as required without the phosphorescent properties of the film being impaired. The film does not contain radioactive materials.

## Release Paper

PE-silicone coated paper, siliconized on one side, 143 g/m<sup>2</sup>

## Adhesive

Solvent polyacrylate, permanent

## Area of use

Ideal for the indoor marking of emergency exits and danger spots.

## Printing Method

Screen printing is recommended.

## Technical Data

<b>Luminous density*</b> (DIN 67510-1:2009)	After 10 min.: 23.0 mcd/m <sup>2</sup> After 60 min.: 3,0 mcd/m <sup>2</sup>
<b>Decay time*</b> (DIN 67510-1:2009)	340 min. (0.3 mcd/m <sup>2</sup> )
<b>Thickness*</b> (without protective paper and adhesive)	150 micron
<b>Weight*</b> (without protective paper and adhesive)	230 g/m <sup>2</sup>
<b>Flammability</b> (DIN 53438 T3)	F1
<b>Dimensional stability</b> (FINAT TM 14)	Adhered to steel, shrinkage 0,3 mm max.
<b>Temperature resistance</b>	Adhered to aluminium, -40° C to +100° C, no variation
<b>Adhesive power*</b> (FINAT TM 1, after 24h, stainless steel)	18 N/25 mm
<b>Tensile strength</b> (DIN EN ISO 527)	Along: > 12 MPa Across: > 10 MPa
<b>Elongation at break</b> (DIN EN ISO 527)	Along: > 100% Across: > 100%
<b>Shelf life**</b>	2 years
<b>Application temperature</b>	> +8° C
<b>Service life by specialist application</b> under vertical indoor application	5 years (not printed, indoor applications)

\* average \*\* in original packaging, at 20° C and 50% relative humidity

## Note

Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any other contamination that could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Furthermore, the application information published by ORAFOL must be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

### **IMPORTANT NOTICE**

All ORALUX® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORALUX® products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of ORALUX® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice.

ORALUX® is a registered trademark of ORAFOL Europe GmbH.